



**REACTION TO FIRE CLASSIFICATION REPORT
N° 2024/182-2**

(English report of classification report N°2024/182-1)

According to EN 13501-1 (2018)

**Notification by the French Government to the European Commission
under n° NB 2401
Regulation (UE) n° 305/2011**

Sponsor : BALSAN
Corbilly Arthon
36330 LE POINCONNET
FRANCE

Product name : Tufted carpet 100% polyamide on woven synthetic backing

Description : Textile floor coverings (EN 1307 family)
(see detailed description in paragraph 2)

Date of issue : 01/10/2024

The indicated classification does not prejudice the conformity of marketed materials with the samples submitted to the tests and under no circumstances, this document should not be considered as type approval or certification of the product in the sense of the L 115-27 article of the consumption's code of the law.

*The reproduction of this classification report is only authorised in its integral form.
It comprises 3 pages*

1. Introduction

This classification report defines the classification assigned to the above-mentioned products in accordance with the procedures given in the NF EN 13501-1 standard (2018).

2. Details of classified product

2.1. Product standard

NF EN 14041 (2005): “Resilient, textile and laminate floor coverings - Essential characteristics”.

2.2. Product description

Tufted carpet 100% polyamide on woven synthetic backing (EN 1307 family).

Tested glued (acrylic glue with depositing 350 g/m²) over a fibre-cement board classified A1_n or A2_n with a density (1800 ± 200) kg/m³ and thickness (8 ± 2) mm.

Use surface : 100 % polyamide

Nominal mass per unit area : 1945 to 2370 g/m²

Nominal effective pile thickness : 5,5 to 8,0 mm

3. Test reports and tests results in support of this classification

3.1. Tests reports

Name of laboratory	Name of sponsor	Test report report N°	Test method
C.R.E.T.	CARUS 99, rue de la Verrerie 75014 PARIS FRANCE	RL 2020/597 RL 2020/600 RL 2020/686 RL 2022/149 RL 2024/274	NF EN ISO 9239-1

3.2. Tests results

Classes of reaction to fire for textile floor coverings, classified without further testing.

Test method NF EN ISO 11925-2	The family product meets the requirements of table 2 of the standard EN 14041 and is classified E _n without further testing (CWFT)
----------------------------------	---

Test method	Product	Number of tests	Parameters	Results
				Continuous parameters : mean value
NF EN ISO 9239-1	Family product	3	Critical heat flux (kW/m ²)	≥ 8,0
			Smoke (% X min)	≤ 750

4. Classification and field of application

4.1. Reference of classification

This classification has been carried out in accordance with EN 13501-1 (2018).

4.2. Classification

Fire behaviour		Smoke production
B _{fl}	-	s1

Classification : B_{fl} – s1

4.3. Field of application

This classification is valid for the following end use applications :

Glued over fibre-cement A1_{fl} or A2_{fl} class with a density $\geq 1350 \text{ kg/m}^3$.

This classification is valid for the following product parameters :

- A nominal mass per unit area of : 1945 to 2370 g/m²
- A nominal effective pile thickness of : 5,5 to 8,0 mm

The classification of the product family is valid for the following trademarks :

COMMODE 800
COMMODE 1000
COMMODE 1200
EMPEROR 1000
EMPEROR 1200
EMPEROR 1450
GOLDEN GATE
GRANDE
SATINE

5. Limitations

This classification document does not represent type approval or certification of the product.

“The classification assigned to the product in this report is appropriate to a declaration of conformity by the manufacturer within the context of system 3 attestation of conformity and CE marking under the Construction Products Directive.

The manufacturer has made a declaration, which is held on file. This confirms that the products design requires no specific processes, procedures or stages (no addition of flame-retardants, limitation of organic content, or addition of fillers) that are aimed at enhancing the fire performance in order to obtain the classification achieved. As a consequence the manufacturer has concluded that system 3 attestation is appropriate.

The test laboratory has, therefore, played no part in sampling the product for the test, although it holds appropriate references, supplied by the manufacturer, to provide for traceability of the samples tested.”

For the SARL C.R.E.T.
The Technical Director
Marc WELCOMME



End of the classification report